

PARAMETERS/UNITS	STANDARD	300	200
Thickness (mm)	EN 964-1	1.8	1.2
Area weight (g/m ²)	EN 965	300	200
Strength MD (kN/m)	EN ISO 10319	25	12
Strength CD (kN/m)	EN ISO 10319	25	12
Elongation MD (%)	EN ISO 10319	50	45
Elongation CD (%)	EN ISO 10319	55	50
CBR puncture resistance (kN)	EN ISO 12236	4	2.6
Cone drop test (mm)	EN 918	10	22
Opening size O ₉₀ (mm)	EN ISO 12956	0.08	0.08
Permeability (m.s ⁻¹)	EN ISO 11058	6*10 ⁻²	0.075

The values correspond to average results obtained and are indicative.

Above mentioned data is informative only.